

Catalyzation Guide based on Material Temperature

Product: **JCore**
 Code # **4502 / 4501**

Product Data

Wt/ga **5.1** lbs/ga **4502 / 4501**
 MEKP **8** lbs/ga **Lupersol DDM-9**
 Avg lbs/pail **24** lbs/pail

Approx. working time at the following initiation levels:

28.00 minutes

Material Temp.	% by wt	gm/qt	gm/ 5 ga	gm/ 5 ga	cc/qt	cc/ga	cc/ 5 ga
70 F	2.00	12	46	222	11	44	213
80 F	1.50	9	35	167	8	33	160
90 F	0.75	4	17	83	4	17	80

The information contained herein is solely for informational purposes. Suitability to task should be determined by user prior to application. For further information check our web site @