

Catalyzation Guide based on Material Temperature

Last Revision: Aug. 05, 2018

Product: Brushable Radius Compd.
Code # 5121

Product Data

Wt/ga	11.2	lbs/ga	5121
MEKP	8	lbs/ga	Norox MEKP-9
Avg lbs/pail	55	lbs/pail	

Approx. working time at the following initiation levels:

40.00 to 60 minutes

Material Temp.	% by wt	gm/ga	gm/ 5 ga	cc/ga	cc/ 5 ga	30ml/shots
50 - 60 F	2.50	127	623	122	598	19.9
60 - 65	2.25	114	561	110	538	17.9
65 - 70	2.00	102	498	98	478	15.9
70 - 75	1.75	89	436	85	419	14.0
75 - 80	1.50	76	374	73	359	12.0
80 - 85	1.25	64	311	61	299	10.0
85 - 90	1.00	51	249	49	239	8.0
90 - 95	0.75	38	187	37	179	6.0

The information contained herein is solely for informational purposes. Suitability to task should be determined by user prior to application. For further information check our web site @

[http:// www.arjaytech.com](http://www.arjaytech.com)