



2018 Product Guide

See our website for additional information: www.ArjayTech.com
 Arjay Technologies • 919.598.2400 A Division of SCIGRIP Adhesives

	Light Weight		Fairing	Fairing Hi-Build	Medium Weight	Radius	Radius Grey	Radius Low Viscosity	Radius AME 5001
Item Number & Availability	1041 (5g)	1701 (5g) 1702 (55g)	1201 (5g)	1301	2011 (5g) 2012 (55g)	2121 (5g)	2121G (5g)	2421 (5g) 2422 (55g)	5121 (5g)
Weight/Gal	6.3	7.9	5.2	6.2	8.6	10.2	10.2	10.6	11.0
Exotherm, °F	242	184	320	325	180	240	253	248	248
Gel Time, min	40	40	6	6	45	21	18	27	60
Pumpable	No	Yes	No	No	Yes	No	No	No	No
Sprayable	No	No	No	No	No	No	No	No	No
Special Notes			MEKP BPO	MEKP BPO					

	Bonding Rigid Sandable	Chopped Glass Critical Bonding	Core Bonding Hand-Applied	Core Filing	Core Bonding Pumpable	J-Core	J-Core High Viscosity	J-Core Putty-Like Viscosity
Item Number & Availability	3201	3401	4001 (5g)	4021 (5g)	4202 (55g)	4501 (5g) 4502 (55g)	4501HV (5g) 4502HV (55g)	4501XHV (5g) 4502XHV (55g)
Weight/Gal	11.5	9.8	6.5	6.6	7.0	5.1	5.1	5.0
Exotherm, °F	254	284	240	238	248	150	156	154
Gel Time, min	24	13	41	28	36	28	36	36
Pumpable	No	No	No	No	Yes	Yes	Yes	Yes
Sprayable	No	No	No	No	No	No	No	No
Special Notes	Industrial Fiber reinforced	5501 - Gel=34	MEKP BPO avail. w/48 pail min	Fills Core Edges			Better hang	

	Molding	Molding Fast Cure	Ceramic Pourable	Vinyl Ester	Vinyl Ester High Fiber	Vinyl Ester Fire Retardant
Item Number & Availability	4701 (5g) 4702 (55g)	4901 (5g) 4902 (55g)	6011 (5g) 6012 (55g)	7121 (5g)	7401 Clear (5g) 7401G Gray (5g)	7401 FRCL (5g)
Weight/Gal	6.7	7.2	7.2	9.8	9.8	9.8
Exotherm, °F	170	284	150	285	320	338
Gel Time, min	28	35	21	35	9	10
Pumpable	Yes	Yes	Yes	Yes	No	No
Sprayable	Yes	Yes	No	No	No	No
Special Notes	Cycle time overnight	Cycle time 2-3 hours		MEKP BPO avail. w/48 pail min	For industrial 15% min glass	Derakane® 510 B-400 Epoxy VE Resin

QUESTIONS?
 You can find information on our products, as well as, ProTips covering best practices and usage on our website at ArjayTech.com.

Feel free to call or email us anytime at:
 919 598 2400
sales@arjaytech.com